

VALOX™ RESIN 325FC

REGION ASIA

DESCRIPTION

Commercial, VALOX 325FC is compliant with food contact regulations. VALOX 325FC is a general purpose, unreinforced PBT injection moulding resin which contains internal mold release. This new 325FC grade is a good processable resin that exhibits faster and more economical cycle times.

TYPICAL PROPERTY VALUES

Revision 20260509

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	60	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	60	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	7	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	15	%	ASTM D638
Tensile Modulus, 50 mm/min	2500	MPa	ASTM D638
Tensile Stress, yield, 50 mm/min	60	MPa	ISO 527
Tensile Stress, break, 50 mm/min	60	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	10	%	ISO 527
Tensile Strain, break, 50 mm/min	15	%	ISO 527
Tensile Modulus, 1 mm/min	2550	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	85	MPa	ISO 178
Flexural Modulus, 2 mm/min	2400	MPa	ISO 178
Ball Indentation Hardness, H358/30	145	MPa	ISO 2039-1
Hardness, Rockwell R	117	-	ISO 2039-2
IMPACT			
Charpy Impact, unnotched, 23°C	NB	kJ/m²	ISO 179/2C
Charpy Impact, unnotched, -30°C	80	kJ/m²	ISO 179/2C
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	NB	J/m	ASTM D4812
Izod Impact, notched, 23°C	38	J/m	ASTM D256
Izod Impact, notched, 0°C	36	J/m	ASTM D256
Izod Impact, notched, -30°C	36	J/m	ASTM D256
Izod Impact, unnotched 80°10'4 +23°C	NB	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80°10'4 -30°C	100	kJ/m²	ISO 180/1U
Izod Impact, notched 80°10'4 +23°C	4	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10'4 0°C	4	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10'4 -30°C	4	kJ/m²	ISO 180/1A
Charpy Impact, notched, 23°C	4	kJ/m²	ISO 179/2C
Charpy Impact, notched, -30°C	4	kJ/m²	ISO 179/2C
THERMAL			
Vicat Softening Temp, Rate A/50	220	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	185	°C	ASTM D1525
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	220	°C	ISO 306

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	185	°C	ISO 306
Vicat Softening Temp, Rate B/120	185	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	150	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	50	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.31	-	ASTM D792
Mold Shrinkage on Tensile Bar, flow	1.3 – 2.0	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	1.1 – 2.0	%	SABIC method
Density	1.31	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.34	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
Melt Volume Rate, MVR at 250°C/2.16 kg	20	cm³/10 min	ISO 1133
Melt Volume Rate, MVR at 250°C/5.0 kg	50	cm³/10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	165	Pa-s	ISO 11443
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	245 – 265	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

