

VALOX™ RESIN 430

REGION AMERICAS

DESCRIPTION

33 % glass reinforced, impact modified. Connectors, etc.

TYPICAL PROPERTY VALUES

Revision 20190924

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	106	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3.1	%	ASTM D638
Tensile Modulus, 5 mm/min	8660	MPa	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	174	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	7810	MPa	ASTM D790
Hardness, Rockwell R	125	-	ASTM D785
IMPACT			
Izod Impact, unnotched, 23°C	857	J/m	ASTM D4812
Izod Impact, notched, 23°C	128	J/m	ASTM D256
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	223	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	208	°C	ASTM D648
Relative Temp Index, Elec	130	°C	UL 746B
Relative Temp Index, Mech w/impact	130	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.52	-	ASTM D792
Specific Volume	0.65	cm³/g	ASTM D792
Water Absorption, (23°C/24hrs)	0.05	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.5	%	SABIC method
Mold Shrinkage, flow, 1.5-3.2 mm	0.3 – 0.5	%	SABIC method
Mold Shrinkage, flow, 3.2-4.6 mm	0.5 – 0.8	%	SABIC method
Mold Shrinkage, xflow, 1.5-3.2 mm	0.4 – 0.6	%	SABIC method
Mold Shrinkage, xflow, 3.2-4.6 mm	0.6 – 0.9	%	SABIC method
Melt Flow Rate, 250°C/2.16 kgf	11.7	g/10 min	ASTM D1238
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D495
Hot Wire Ignition {PLC}	0	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	0	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	2	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-220794	-	-
UL Recognized, 94HB Flame Class Rating	1.47	mm	UL 94
INJECTION MOLDING			

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 265	°C	
Nozzle Temperature	245 – 260	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

