

VALOX™ RESIN 732E

REGION AMERICAS

DESCRIPTION

30% glass/mineral reinforced, excellent thermal performance, low shrinkage and warp. Easy flow.

TYPICAL PROPERTY VALUES

Revision 20260318

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	82	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	124	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	6890	MPa	ASTM D790
Hardness, Rockwell R	109	-	ASTM D785
IMPACT			
Izod Impact, unnotched, 23°C	534	J/m	ASTM D4812
Izod Impact, notched, 23°C	101	J/m	ASTM D256
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	215	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	198	°C	ASTM D648
CTE			
-40°C to 40°C, flow	2.52E-05	1/°C	ASTM E831
60°C to 138°C, flow	2.52E-05	1/°C	ASTM E831
PHYSICAL			
Melt Flow Rate, 265°C/2.16kgf	16.5	g/10 min	ASTM D1238
Specific Gravity	1.51	-	ASTM D792
Specific Volume	0.66	cm³/g	ASTM D792
Water Absorption, (23°C/24hrs)	0.07	%	ASTM D570
Mold Shrinkage, flow, 1.5-3.2 mm	0.3 – 0.4	%	SABIC method
Mold Shrinkage, flow, 3.2-4.6 mm	0.4 – 0.6	%	SABIC method
Mold Shrinkage, xflow, 1.5-3.2 mm	0.4 – 0.6	%	SABIC method
Mold Shrinkage, xflow, 3.2-4.6 mm	0.6 – 0.8	%	SABIC method
ELECTRICAL			
Volume Resistivity	1.E+17	Ω.cm	ASTM D257
Dielectric Strength, in oil, 3.2 mm	17.9	kV/mm	ASTM D149
Relative Permittivity, 50/60 Hz	3.53	-	ASTM D150
Relative Permittivity, 1 MHz	3.32	-	ASTM D150
Dissipation Factor, 50/60 Hz	0.008	-	ASTM D150
Dissipation Factor, 1 MHz	0.013	-	ASTM D150
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-477264	-	-
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	255 – 275	°C	
Nozzle Temperature	255 – 270	°C	
Front - Zone 3 Temperature	255 – 265	°C	
Middle - Zone 2 Temperature	250 – 260	°C	
Rear - Zone 1 Temperature	245 – 255	°C	
Mold Temperature	65 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

